

# Neromin Synthetic Enamel (IS 2932 PQ)

## Scope

It is recommended to apply over metal surfaces and primed concrete surface after appropriate surface preparation.

## Composition

Synthetic, alkyd based enamel.

Volume solids	28 ± 3%
DFT / Coat	25 - 30 µ
Theoretical Coverage / Coat	9.33 – 11.20 m <sup>2</sup> / ltr.

## Product Details

Type	Single Pack
Colour	In desired shades
Gloss	Glossy
Flash Point	Above 30° C
Drying Time (30°C)	
Surface Dry	Max. 6 Hrs.
Hard Dry	Max. 24 Hrs.
Recoating Time	Overnight
Thinner	T-047
Thinner Consumption	
Conventional Spray	5 – 20%
Brush	0 – 20%

## Application Details

**Applied over:**  
Metal / Concrete.

**Application Method:**  
Brush / conventional spray

**Shelf Life:**  
12 months under normal storage condition in original sealed containers at 30°C

**Pack Size:**  
20 ltrs.

**Surface Preparation:**  
Primed surface must be clean, dry, and free from moisture, grease or other contaminants.

**Application Instruction:**  
If settling is observed in the drum, loosen the settled material & mix with pneumatic stirrer till homogeneous.

**Environmental Conditions:**  
Surface temperature must be at least 3°C above Dew Point to prevent condensation.

### Temperature:

Air	5 - 40°C
Surface	5 - 50°C

**Special Notes:**  
Thinner consumption may vary depending upon site conditions. Practical covering capacity depends on application techniques, ambient conditions, wastage, surface condition etc.

**Safety Precautions:**  
Please refer to the Material Safety Data Sheet.

**Kansai Nerolac Paints (KNP)** warrants the goods to be free from defects in material and workmanship. KNP makes no other warranties concerning the goods. No other warranties, whether expressed, implied or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply to goods and in no event shall KNP be liable for consequential or incidental damages. Any recommendation or suggestion relating to use of the products made by KNP whether in the technical literature of KNP, or in response to specific inquiry, or otherwise, is based on data believed to be reliable by KNP, and KNP shall not be liable for any loss or damage incurred to the Buyer on account thereof. However, the goods and information are intended for use by the Buyer having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy himself of the suitability of the goods for his own particular use and it shall be deemed that the Buyer has done so, at his sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results".  
Issue Date: October 15, 2006  
PN: 25090-01